

锂电池 UN38.3 测试报告

Lithium Battery UN38.3 Test Report

委托单位: 广东力德诺电子科技有限公司

Applicant: Guang Dong LDNIO Electronic Technology Co., Ltd.

货物名称: 无线耳机充电盒 T13 300mAh 1.11Wh

Name Of

Wireless Earbuds Charging Base T13 300mAh 1.11Wh

Goods:

测试机构: 深圳市元素检测有限公司

Testing By: Shenzhen Element Testing Co., Ltd.

测试机构地址:

深圳市龙岗区坪地街道坪西社区龙岭北路76号2号厂房401、4号厂房101 邮编518117

Testing

Institution

101 of Plant 4, & 401 of Plant 2, No.76, Longling North Road, Pingxi, Pingdi

Address:

Subdistrict, Longgang District, Shenzhen, Guangdong, China/518117

签发日期:

2025-06-04

Issue Date:


主检人: 廖铭韬/测试工程师

Tested By: Mint Liao/Test Engineer

 廖铭韬 Mint Liao

审核人: 叶小媚/项目工程师

Checked By: April Ye/Project Engineer

 叶小媚 April Ye

深圳市元素检测有限公司
Shenzhen Element Testing Co., Ltd.

批准人: 卢敏/技术负责人

Approved By: Jerry Lu/Technical Director

 卢敏 Jerry Lu



样品名称 Sample name	无线耳机充电盒 Wireless Earbuds Charging Base		型号 Model	T13	
商标 Brand	/		检测类别 Test Classification	委托测试 COMMISSION TEST	
报告编号 Report no.	ELE2505B01094				
委托单位 Applicant	广东力德诺电子科技有限公司 Guang Dong LDNIO Electronic Technology Co., Ltd.				
	广东省佛山市南海区桂城街平州工业园区 B 区胜利东路 6 号厂房 A、B、C 栋 Factory building A, building B and building C, No.6 Shengli East Road, Pingzhou Industrial Park B zone, Guicheng Street, Nanhai District, Foshan City, Guangdong Province, China				
制造单位 Manufacturer	广东力德诺电子科技有限公司 Guang Dong LDNIO Electronic Technology Co., Ltd.				
	广东省佛山市南海区桂城街平州工业园区 B 区胜利东路 6 号厂房 A、B、C 栋 Factory building A, building B and building C, No.6 Shengli East Road, Pingzhou Industrial Park B zone, Guicheng Street, Nanhai District, Foshan City, Guangdong Province, China				
电话 Telephone	+86- 13724537943	邮箱 Email	351940529@q q.com	网址 Website	/
测试日期 Tested Date	2025-05-20~2025-06-04				
试验依据 Test Method	联合国《试验和标准手册》（第八修订版）38.3 节 UN "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.8/Subsection 38.3				
测试结论 Test Conclusion: 该电池样品通过所有项目检测，符合该条款的性能要求。 The samples have passed all test items.					
 深圳市元素检测有限公司 Shenzhen Element Testing Co., Ltd. (盖章 stamp)					
检测日期： Tested Date:	2025-05-20	审核日期： Checked Date:	2025-06-04	批准日期： Approved Date:	2025-06-04

I、样品描述 Sample Description			
型号 Model	T13	标称电压 Nominal Voltage	DC: 5.0V Battery: 3.7V
额定容量 Rated capacity	300mAh	额定能量 Rated Energy	1.11Wh
标准充电电流 Standard Charge Current	60mA	标准放电电流 Standard Discharge Current	60mA
最大充电电流 Max. Charge Current	300mA	最大放电电流 Max. Discharge Current	300mA
充电限制电压 Max. Charging Voltage	5.0V	充电截止电流 End Charge Current	--
放电截止电压 Cut-off Voltage	--	外观形状 Appearance	黑色近长方体 Approximate Black Cuboid
电池尺寸 Battery Dimension (LxWxT)	(64.6x49.8x28.1)mm	电池质量 Battery Mass	31.04g
电池芯型号 Cell model	701530	电池芯标称电压 Cell Nominal Voltage	3.7V
电池芯额定容量 Cell Rated capacity	300mAh	电池芯额定能量 Cell Rated Energy	1.11Wh
电池芯数量 Cell Number	1PC	电池芯外观形状 Cell Appearance	银色近长方体 Approximate Silver Cuboid

II、测试程序 Test Procedure

1. 每一种类型的电池均应进行 T.1 至 T.8 项试验。电池必须按顺序在相同的一组电池上进行试验 T.1 至 T.5。试验 T.6 和 T.8 应使用未另外试验过的电池。试验 T.7 可以使用先前在试验 T.1 至 T.5 中使用过的未损坏电池进行，以便测试进行在循环过的电池上。

Each battery type is subjected to tests T.1 to T.8. Tests T.1 to T.5 are conducted in sequence on the same battery. Tests 6 and 8 are conducted using not otherwise tested batteries. Test T.7 may be conducted using undamaged batteries previously used in Tests T.1 to T.5 for purposes of testing on cycled batteries.

2. 为了量化质量损失，可用以下公式计算：质量损失(%)=(M1-M2)/M1×100

In order to quantify the mass loss, the following procedure is provided: Mass loss(%)=(M1-M2)/M1×100
 式中：M1是试验前的质量，M2是试验后的质量。如果质量损失不超过下表所列的数值，应视为“无质量损失”。

Where M1 is the mass before the test and M2 is the mass after the test. When mass loss does not exceed the values in Table below, it is considered as "no mass loss".

电芯或电池的质量 Mass M of cell or battery	质量损失限值 Mass loss limit
M < 1g	0.5%
1g ≤ M ≤ 75g	0.2%
M > 75g	0.1%

3. 在测试 T.1 至 T.4 中，电池须满足无渗漏、无泄气、无解体、无破裂和无起火，并且每个试验电池在试验后的开路电压不小于其在进行这一试验前电压的90%。

In test T.1 to T.4, batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test battery after testing is not less than 90% of its voltage immediately prior to this procedure.

III、一般说明 General description

本报告出现的试验结果仅与试验样品有关。

The test results presented in this report relate only to the object tested.

除非全部复制，否则无试验室书面批准本报告不得部分复制。

This report shall not be reproduced, except in full, without the written approval of the Issuing testing laboratory.

可能的试验情况判定 / Possible test case verdicts:	
一 试验情况不适用本试验产品 — Test case does not apply to the test object	不适用 N/A (Not applicable)
一 试验样品满足要求 — Test object does meet the requirement	通过 P (Passed)
一 试验样品不满足要求 — Test object does not meet the requirement	失败 F (Fail)

IV、测试项目及样品编号描述

Test items description and number of the sample:

测试项目 Test items	样品编号 Sample Number
T.1: 高度模拟/Altitude simulation	电池组/batteries: B01~B10
T.2: 温度测试/ Thermal test	
T.3: 振动/ Vibration	
T.4: 冲击/ Shock	
T.5: 外短路/External short circuit	
T.6: ☑挤压 Crush □撞击 Impact	电池/cells: C01~C10
T.7 过度充电/ Overcharge	电池组/batteries: B11~B18
T.8: 强制放电/ Forced discharge	电池/cells:C11~C30

V、样品预处理状态描述说明

Pre-treatment status description and illustration of sample:

测试项目 Test item	样品编号 Sample No.	预处理状态 Pre-treatment state	备注 Remark
T.1~T.5	B01~B05	在第一次循环完全充电状态。 At first cycle, in fully charged states.	---
	B06~B10	在25次循环结束后完全充电状态。 After 25 cycles ending in fully charged states.	---
T.6	C01~C05	在第一次循环50%额定容量的荷电状态。 At first cycle at 50% of the design rated capacity.	---
	C06~C10	在25次循环结束后50%额定容量的荷电状态。 After 25 cycles ending at 50% of the design rated capacity.	---
T.7	B11~B14	在第一次循环完全充电状态。 At first cycle, in fully charged states.	---
	B15~B18	在25次循环结束后完全充电状态。 After 25 cycles ending in fully charged states.	---
T.8	C11~C20	在第一次循环完全放电状态。 At first cycle, in fully discharged states.	---
	C21~C30	在25次循环结束后完全放电状态。 After 25 cycles ending in fully discharged states.	---

备注: 送检样品符合《联合国试验和标准手册》(ST/SG/AC.10/11/Rev.8), 38.3章的要求。

Remark: The samples submitted for inspection meet the requirements of the UN "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.8/Subsection 38.3.

VI、测试方法 Test methods			
ST/SG/AC.10/11/Rev.8/Subsection 38.3.			
条款/Clause	标准要求/ Requirement + Test	测试结果 / Result	判定/ Verdict
38.3.4.1	Test T.1: 高度模拟 Altitude simulation		P
	试验电池和电池组应在压力等于或低于 11.6 千帕和环境温度(20±5℃)下存放至少 6 小时。 Test cells and batteries shall be stored at a pressure of 11.6 kPa or less for at least six hours at ambient temperature (20 ± 5 °C).		P
	要求电池和电池组无渗漏、无排气、无解体、无破裂和无起火,并且每个试验电池或电池组在试验后的开路电压不小于其在进行这一试验前电压的90%。有关电压的要求不适用于完全放电状态的试验电池和电池组。Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90 % of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.	无质量损失、无漏液、无泄气、无分解、无破裂、无着火,且测试后开路电压大于测试前开路电压的90%。 测试数据见表格T.1 No mass loss, no leakage, no venting, no disassembly, no rupture and no fire, also open circuit voltage after testing is more than 90% of its initial voltage. Test data see table T.1	P
38.3.4.2	Test T.2: 温度试验 Thermal test		P
	首先将样品放在72±2℃的环境中放置至少6个小时,然后放在-40±2℃的环境中放置至少6个小时。温度转换的最大间隔时间为30分钟。如此循环10次,最后将样品放在20±5℃的环境中静置24小时。Test cells and batteries are to be stored for at least six hours at a test temperature equal to 72 ±2 °C, followed by storage for at least six hours at a test temperature equal to - 40 ± 2 °C. The maximum time interval between test temperature extremes is 30 minutes. This procedure is to be repeated until 10 total cycles are complete, after which all test cells and batteries are to be stored for 24 hours at ambient temperature (20 ± 5 °C).		P
	对于大型电池和电池组,暴露于极端试验温度的时间至少应为12小时。 For large cells and batteries the duration of exposure to the test temperature extremes should be at least 12 hours.		N/A

	<p>要求电池和电池组无渗漏、无排气、无解体、无破裂和无起火，并且每个试验电池或电池组在试验后的开路电压不小于其在进行这一试验前电压的90%。有关电压的要求不适用于完全放电状态的试验电池和电池组。Cells and batteries meet this requirement if there is no mass loss, no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.</p>	<p>无质量损失、无漏液、无泄气、无分解、无破裂、无着火，且测试后开路电压大于测试前开路电压的90%。 测试数据见表格T.2 No mass loss, no leakage, no venting, no disassembly, no rupture and no fire, also open circuit voltage after testing is more than 90% of its initial voltage. Test data see table T.2</p>	P
38.3.4.3	Test T.3: 振动 Vibration		P
	<p>电池和电池组紧固于振动机平台,但不得造成电池变形,并能准确可靠地传播振动。振动应是正弦波形,对数扫描频率在7赫兹和200·赫兹之间,再回到7赫兹,跨度为15分钟。这一振动过程须对三个互相垂直的电池安装方位的每一方向重复进行12次,总共为时3小时。其中一个振动方向必须与端面垂直。Cells and batteries are firmly secured to the platform of the vibration machine without distorting the cells in such a manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal waveform with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting positions of the cell. One of the directions of vibration must be perpendicular to the terminal face.</p>		P
	<p>作对数式频率扫描,对总质量不足12千克的电池和电池组(电池·和小型电池组),和对12千克及更大的电池组(大型电池组)有所不同。The logarithmic frequency sweep shall differ for cells and batteries with a gross mass of not more than 12 kg (cells and small batteries), and for batteries with a gross mass of more than 12 kg (large batteries).</p>		P

	<p>对电池和小型电池组:从7赫兹开始,保持1gn的最大加速度,直到频率达到 18 赫兹。然后将振幅保持在 0.8 毫米 (总偏移 1.6 毫米),并增加频率直到最大加速度达到8gn(频率约为50赫兹)。将最大加速度保持在 8gn 直到频率增加到 200 赫兹。 For cells and small batteries: from 7 Hz a peak acceleration of 1 gn is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 8 gn occurs (approximately 50 Hz). A peak acceleration of 8 gn is then maintained until the frequency is increased to 200 Hz.</p>		<p>P</p>
	<p>对大型电池组:从7赫兹开始,保持1gn的最大加速度,直到频率达到 18 赫兹。然后将振幅保持在 0.8 毫米 (总偏移 1.6 毫米), 并增加频率直到最大加速度达到 2gn (频率约为 25 赫兹)。将最大加速度保持在2gn直到频率增加到200赫兹。 For large batteries: from 7 Hz to a peak acceleration of 1 gn is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 2 gn occurs (approximately 25 Hz). A peak acceleration of 2 gn is then maintained until the frequency is increased to 200Hz.</p>		<p>N/A</p>
	<p>要求电池和电池组试验中和试验后无渗漏、无排气、无解体、无破裂和无起火, 并且每个试验电池或电池组在第三个垂直安装方位上的 • 试验后立即测得的开路电压不小于在进行这一试验前电压的90%。有关电压的要求不适用于完全放电状态的试验电池和电池组。 Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire during the test and after the test and if the open circuit voltage of each test cell or battery directly after testing in its third perpendicular mounting position is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.</p>	<p>无质量损失、无漏液、无泄气、无分解、无破裂、无着火, 且测试后开路电压大于测试前开路电压的90%。 测试数据见表格T.3 No mass loss, no leakage, no venting, no disassembly, no rupture and no fire, also open circuit voltage after testing is more than 90% of its initial voltage. Test data see table T.3</p>	<p>P</p>

38.3.4.4	Test T.4: 冲击 Shock		P									
	试验电池和电池组用坚硬支架紧固在试验装置上,支架支撑着每个试验电池组的所有安装面。每个电池需经受最大加速度150gn和脉冲持续时间6毫秒的半正弦波冲击。针对大型电池需经受最大加速度50gn和脉冲持续时间11毫秒的半正弦波冲击。 Test cells and batteries shall be secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery. Each cell shall be subjected to a half-sine shock of peak acceleration of 150gn and pulse duration of 6 milliseconds. Alternatively, large cells may be subjected to a half-sine shock of peak acceleration of 50g, and pulse duration of 11 milliseconds.		P									
	每个电池组应根据电池组的质量而受到峰值加速度的半正弦波冲击。对于小型电池组的脉冲持续时间应6毫秒,对于大型电池组的脉冲持续时间应为11毫秒,下面的公式用于计算适当的最小峰值加速度。 Each battery shall be subjected to a half-sine shock of peak acceleration depending on the mass of the battery. The pulse duration shall be 6 milliseconds for small batteries and 11 milliseconds for large batteries. The formulas below are provided to calculate the appropriate minimum peak accelerations. <table border="1" data-bbox="352 1162 900 1576"> <thead> <tr> <th data-bbox="352 1162 472 1256">电池 Battery</th> <th data-bbox="472 1162 767 1256">最小峰值加速度 Minimum peak acceleration</th> <th data-bbox="767 1162 900 1256">脉冲持续时间 Pulse duration</th> </tr> </thead> <tbody> <tr> <td data-bbox="352 1256 472 1397">小型电池 Small batteries</td> <td data-bbox="472 1256 767 1397">150gn 或公式结果中的较小值 150gn or result of formula $\text{Acceleration (g}_n\text{)} = \sqrt{\frac{100850}{\text{mass}}}$ whichever is smaller</td> <td data-bbox="767 1256 900 1397">6毫秒 6ms</td> </tr> <tr> <td data-bbox="352 1397 472 1538">大型电池 Large batteries</td> <td data-bbox="472 1397 767 1538">50gn 或公式结果中的较小值 50gn or result of formula $\text{Acceleration (g}_n\text{)} = \sqrt{\frac{3000}{\text{mass}}}$ whichever is smaller</td> <td data-bbox="767 1397 900 1538">11毫秒 11ms</td> </tr> </tbody> </table> <p data-bbox="352 1538 900 1576">* 质量单位用于克计算 Mass is expressed in kilograms.</p>	电池 Battery	最小峰值加速度 Minimum peak acceleration	脉冲持续时间 Pulse duration	小型电池 Small batteries	150gn 或公式结果中的较小值 150gn or result of formula $\text{Acceleration (g}_n\text{)} = \sqrt{\frac{100850}{\text{mass}}}$ whichever is smaller	6毫秒 6ms	大型电池 Large batteries	50gn 或公式结果中的较小值 50gn or result of formula $\text{Acceleration (g}_n\text{)} = \sqrt{\frac{3000}{\text{mass}}}$ whichever is smaller	11毫秒 11ms		P
电池 Battery	最小峰值加速度 Minimum peak acceleration	脉冲持续时间 Pulse duration										
小型电池 Small batteries	150gn 或公式结果中的较小值 150gn or result of formula $\text{Acceleration (g}_n\text{)} = \sqrt{\frac{100850}{\text{mass}}}$ whichever is smaller	6毫秒 6ms										
大型电池 Large batteries	50gn 或公式结果中的较小值 50gn or result of formula $\text{Acceleration (g}_n\text{)} = \sqrt{\frac{3000}{\text{mass}}}$ whichever is smaller	11毫秒 11ms										
	每个电池或电池组需在三个互相垂直的安装方位的正方向经受三次冲击,接着在反方向经受三次冲击,总共经受18次冲击。 Each cell or battery is subjected to three shocks in the positive direction followed by three shocks in the negative direction of each of three mutually perpendicular mounting positions of the cell for a total of 18 shocks.		P									

	<p>要求电池和电池组无渗漏、无排气、无解体、无破裂和无起火，并且每个试验电池或电池组在试验后的开路电压不小于其在进行这一试验前电压的90%。有关电压的要求不适用于完全放电状态的试验电池和电池组。Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90 % of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.</p>	<p>无质量损失、无漏液、无泄气、无分解、无破裂、无着火，且测试后开路电压大于测试前开路电压90%。测试数据见表格T.4。 No mass loss, no leakage, no venting, no disassembly, no rupture and no fire, also open circuit voltage after testing is more than 90% of its initial voltage. Test data see table T.4</p>	P
38.3.4.5	Test T.5: 外部短路 External short circuit		P
	<p>待测试的电池或电池组应加热一段时间，使其外表面温度达到均匀稳定的$57 \pm 4^\circ\text{C}$的温度。加热时间取决于电池或电池组的大小和设计，并应进行评估和记录。如果这种评估是不可行的，对于小型电池和小型电池组至少在$57 \pm 4^\circ\text{C}$的环境下存放 6 小时，对于大型电池和大型电池组至少在$57 \pm 4^\circ\text{C}$的环境下存放12小时。然后电池或电池组在$57 \pm 4^\circ\text{C}$的环境中，应接受一个外部总阻值小于 0.1 欧姆的短路条件。The cell or battery to be tested shall be heated for a period of time necessary to reach a homogeneous stabilized temperature of $57 \pm 4^\circ\text{C}$, measured on the external case. This period of time depends on the size and design of the cell or battery and should be assessed and documented. If this assessment is not feasible, the exposure time shall be at least 6 hours for small cells and small batteries, and 12 hours for large cells and large batteries. Then the cell or battery at $57 \pm 4^\circ\text{C}$ shall be subjected to one short circuit condition with a total external resistance of less than 0.1 ohm.</p>		P
	<p>这一短路条件应在电池或电池组的外壳温度回到 $57 \pm 4^\circ\text{C}$后继续短路 1 小时，或对于大型电池组其外壳温度已下降了一半的最大升温，并保持低于该值。短路和冷却过程至少在环境温度中进行。This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to $57 \pm 4^\circ\text{C}$, or in the case of the large batteries, has decreased by half of the maximum temperature increase observed during the test and remains below that value.</p>		P

	<p>要求电池和电池组外壳温度不超过170°C,并且在试验过程中及试验后6小时内无解体,无破裂,无起火。Cells and batteries meet this requirement if their external temperature does not exceed 170 °C and there is no disassembly, no rupture and no fire during the test and within six hours after the test.</p>	<p>外表温度小于170°C, 在测试中及之后6小时内, 无发生分解、破裂和着火。 测试数据见表格T.5 External temperature is less than 170°C, also no disassembly, no rupture and no fire during the test and within six hours after the test. Test data see table T.5</p>	P
38.3.4.6	Test T.6: <input type="checkbox"/> 撞击 Impact <input checked="" type="checkbox"/> 挤压 Crush		P
	<p>撞击(适合于直径大于或等于18mm的圆柱形电池)Test procedure – Impact (applicable to cylindrical cells greater than or equal to 18 mm in diameter)</p>		N/A
	<p>将样品放在一个平坦的光滑平面上。将一直径为15.8 mm±0.1mm, 长度不小于6cm的316不锈钢棒横过样品中部放置后, 将一质量为9.1 kg±0.1 kg的重物从61±2.5 cm的高度落向样品。 The sample cell or component cell is to be placed on a flat smooth surface. A 15.8 mm±0.1mm diameter, at least 6 cm long, or the longest dimension of the cell, whichever is greater, Type 316 stainless steel bar is to be placed across the centre of the sample. A 9.1 kg±0.1 kg mass is to be dropped from a height of 61±2.5 cm at the intersection of the bar and sample in a controlled manner using a near frictionless, vertical sliding track or channel with minimal drag on the falling mass. The vertical track or channel used to guide the falling mass shall be oriented 90 degrees from the horizontal supporting surface.</p>		N/A
	<p>接受撞击的样品, 纵轴应与平坦的表面平行并与横放在样品中心的直径15.8 mm±0.1mm弯曲表面的纵轴垂直。每一个样品只接受一次撞击。 The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8 mm±0.1mm diameter curved surface lying across the centre of the test sample. Each sample is to be subjected to only a single impact.</p>		N/A
	<p>挤压(适用于棱柱形、袋状、硬币/纽扣电池和直径不超过18mm的圆柱形电池)。Test Procedure – Crush (applicable to prismatic, pouch, coin/button cells and cylindrical cells not more than 18 mm in diameter).</p>		P



	<p>将电池或元件电池放在两个平面之间挤压，挤压力度逐渐加大，在第一个接触点上的速度大约为1.5厘米/秒。挤压持续进行，直到出现以下三种情况之一： A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5 cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached:</p>		P
	<p>(a) 施加力达到13kN±0.78kN。The applied force reaches 13kN±0.78kN ;</p>		P
	<p>(b) 电池的电压下降至少100mV。The voltage of the cell drops by at least 100 mV;</p>		N/A
	<p>(c) 电池变形达原始厚度的50%或以上。The cell is deformed by 50% or more of its original thickness.</p>		N/A
	<p>棱柱形或袋装电池应从最宽的一面施压。纽扣/硬币形电池应从其平坦表面施压。圆柱形电池应从与纵轴垂直的方向施压。A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis.</p>		P
	<p>每个试样电池或元件电池只做一次挤压试验。试样应继续观察6小时。试验应使用之前未做过其他试验的电池或元件电池进行。Each test cell or component cell is to be subjected to one crush only. The test sample shall be observed for a further 6 h. The test shall be conducted using test cells or component cells that have not previously been subjected to other tests.</p>		P
	<p>要求电池和原件电池外壳温度不超过 170°C，并且在试验过程中及试验后6小时内无解体,无起火。Cells and component cells meet this requirement if their external temperature does not exceed 170°C and there is no disassembly and no fire during the test and within six hours after this test.</p>	<p>电池外表温度小于170°C，在测试中及之后6小时内无发生分解和着火。 测试数据见表格T.6 External temperature of cells is less than 170°C, also no disassembly and no fire during the test and within six hours after the test. Test data see table T.6</p>	P

38.3.4.7	Test T.7: 过度充电 Overcharge		P
	在室温下, 以2倍的制造商宣称的最大持续充电电流对样品充电, 测试时间为24小时。测试的最小电压如下: The charge current shall be twice the manufacturer's recommended maximum continuous charge current. Tests are to be conducted at ambient temperature. The duration of the test shall be 24 hours. The minimum voltage of the test shall be as follows:		P
	(a) 如果制造商宣称的充电电压不超过18V, 本测试的最小充电电压应是制造商宣称的最大充电电压的两倍或者是22V之中的较小者。When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V.		P
	(b) 如果制造商宣称的充电电压超过18V, 本测试的最小充电电压应该是制造商宣称的最大充电电压的1.2倍。When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage.		N/A
	要求充电电池组在试验过程中和试验后7天内无解体,无起火。There is no disassembly and no fire during the test and within seven days after the test.	在测试中和测试完成后7天内无发生分解和着火。测试数据见表格T.7 No disassembly and no fire during the test and within seven days after the test Test data see table T.7	P
38.3.4.8	Test T.8: 强制放电 Forced discharge		P
	每个电池应在环境温度下与12V直流电源上进行强制放电,此直流电源串联在起始电流等于制造商给定的最大放电电流条件下强制放电。Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12V D.C. power supply at an initial current equal to the maximum discharge current specified by the manufacturer. 将适当大小和额定值的电阻负荷与试验电池串联, 计算得出给定的·放电电流。对每个电池进行强制放电,放电时间(小时)应等于其额定容量除以初始试验电流(安培)。The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell shall be forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere).		P



	<p>要求原电池或充电电池在试验过程中和试验后7天内无解体,无起火。There is no disassembly and no fire during the test and within seven days after the test.</p>	<p>电池在测试中和测试完成后7天内无发生分解和着火。 测试数据见表格T.8 Cells have no disassembly and no fire during the test and within seven days after the test. Test data see table T.8</p>	<p>P</p>
--	---	--	----------

VI、测试数据 Test Data
T.1. 高度模拟 Altitude simulation

样品状态 The state of samples	编号 No.	试验前 Pre-test		试验后 After test		质量损失 Mass loss (%)	电压比 (%) Voltage ratio	测试结果 Test result
		质量 Mass (g)	电压 Voltage (V)	质量 Mass (g)	电压 Voltage (V)			
在第一次循环完全充电状态 At first cycle, in fully charged states	B01	31.039	5.112	31.039	5.112	0.000	100.000	P
	B02	30.158	5.109	30.158	5.109	0.000	100.000	P
	B03	30.518	5.128	30.518	5.128	0.000	100.000	P
	B04	30.545	5.125	30.545	5.125	0.000	100.000	P
	B05	30.070	5.133	30.070	5.133	0.000	100.000	P
在25次循环结束后完全充电状态 After 25 cycles ending in fully charged states	B06	30.480	5.118	30.480	5.118	0.000	100.000	P
	B07	30.478	5.117	30.478	5.117	0.000	100.000	P
	B08	30.326	5.127	30.326	5.127	0.000	100.000	P
	B09	30.453	5.106	30.453	5.106	0.000	100.000	P
	B10	30.249	5.114	30.249	5.114	0.000	100.000	P

注释 Notes :

测试后, 样品无渗漏、无排气、无解体、无破裂和无起火, 电压比不小于 90%。After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And voltage ratio is not less than 90%.

T.2. 温度试验 Thermal test

样品状态 The state of samples	编号 No.	试验前 Pre-test		试验后 After test		质量损失 Mass loss (%)	电压比 (%) Voltage ratio	测试结果 Test result
		质量 Mass (g)	电压 Voltage (V)	质量 Mass (g)	电压 Voltage (V)			
在第一次循环完全充电状态 At first cycle, in fully charged states	B01	31.039	5.112	31.038	5.109	0.003	99.941	P
	B02	30.158	5.109	30.157	5.105	0.003	99.922	P
	B03	30.518	5.128	30.517	5.124	0.003	99.922	P
	B04	30.545	5.125	30.544	5.121	0.003	99.922	P
	B05	30.070	5.133	30.069	5.129	0.003	99.922	P
在25次循环结束后完全充电状态 After 25 cycles ending in fully charged states	B06	30.480	5.118	30.479	5.114	0.003	99.922	P
	B07	30.478	5.117	30.477	5.113	0.003	99.922	P
	B08	30.326	5.127	30.325	5.123	0.003	99.922	P
	B09	30.453	5.106	30.452	5.102	0.003	99.922	P
	B10	30.249	5.114	30.248	5.109	0.003	99.902	P

注释 Notes :

测试后, 样品无渗漏、无排气、无解体、无破裂和无起火, 电压比不小于 90%。After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And voltage ratio is not less than 90%.

T.3. 振动 Vibration

样品状态 The state of samples	编号 No.	试验前 Pre-test		试验后 After test		质量 损失 Mass loss (%)	电压比(%) Voltage ratio	测试结果 Test result
		质量 Mass (g)	电压 Voltage (V)	质量 Mass (g)	电压 Voltage (V)			
在第一次循环完全充电状态 At first cycle, in fully charged states	B01	31.038	5.109	31.038	5.109	0.000	100.000	P
	B02	30.157	5.105	30.157	5.105	0.000	100.000	P
	B03	30.517	5.124	30.517	5.124	0.000	100.000	P
	B04	30.544	5.121	30.544	5.121	0.000	100.000	P
	B05	30.069	5.129	30.069	5.129	0.000	100.000	P
在25次循环结束后完全充电状态 After 25 cycles ending in fully charged states	B06	30.479	5.114	30.479	5.114	0.000	100.000	P
	B07	30.477	5.113	30.477	5.113	0.000	100.000	P
	B08	30.325	5.123	30.325	5.123	0.000	100.000	P
	B09	30.452	5.102	30.452	5.102	0.000	100.000	P
	B10	30.248	5.109	30.248	5.109	0.000	100.000	P
注释 Notes : 测试后, 样品无渗漏、无排气、无解体、无破裂和无起火, 电压比不小于 90%。After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And voltage ratio is not less than 90%.								

T.4. 冲击 Shock

样品状态 The state of samples	编号 No.	试验前 Pre-test		试验后 After test		质量 损失 Mass loss (%)	电压比(%) Voltage ratio	测试结果 Test result
		质量 Mass (g)	电压 Voltage (V)	质量 Mass (g)	电压 Voltage (V)			
在第一次循环完全充电状态 At first cycle, in fully charged states	B01	31.038	5.109	31.038	5.109	0.000	100.000	P
	B02	30.157	5.105	30.157	5.105	0.000	100.000	P
	B03	30.517	5.124	30.517	5.124	0.000	100.000	P
	B04	30.544	5.121	30.544	5.121	0.000	100.000	P
	B05	30.069	5.129	30.069	5.129	0.000	100.000	P
在25次循环结束后完全充电状态 After 25 cycles ending in fully charged states	B06	30.479	5.114	30.479	5.114	0.000	100.000	P
	B07	30.477	5.113	30.477	5.113	0.000	100.000	P
	B08	30.325	5.123	30.325	5.123	0.000	100.000	P
	B09	30.452	5.102	30.452	5.102	0.000	100.000	P
	B10	30.248	5.109	30.248	5.109	0.000	100.000	P
注释 Notes : 测试后, 样品无渗漏、无排气、无解体、无破裂和无起火, 电压比不小于 90%。After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And voltage ratio is not less than 90%.								

T.5. 外部短路 External short circuit

样品状态 The state of samples	编号 No.	样品表面最高温度(°C) Max. External Temperature(°C)	测试结果 Test result
在第一次循环完全充电状态 At first cycle, in fully charged states	B01	57.5	P
	B02	57.3	P
	B03	57.8	P
	B04	57.9	P
	B05	57.4	P
在25次循环结束后完全充电状态 After 25 cycles ending in fully charged states	B06	57.6	P
	B07	57.3	P
	B08	57.6	P
	B09	57.1	P
	B10	57.2	P

注释 Notes :

测试样品表面温度不超过 170 °C，测试中与测试后 6 小时内无解体、无破裂、无起火。Test sample external temperature does not exceed 170 °C and there is no disassembly, no rupture and no fire during the test and within six hours after the test.

T.6. □ 撞击 Impact ☑ 挤压 Crush

样品状态 The state of samples	编号 No.	样品表面最高温度(°C) Max. External Temperature(°C)	测试结果 Test result
在第一次循环50%额定容量的荷电状态 At first cycle at 50% of the design rated capacity	C01	23.4	P
	C02	23.4	P
	C03	23.1	P
	C04	23.4	P
	C05	23.2	P
在25次循环结束后50%额定容量的荷电状态 After 25 cycles ending at 50% of the design rated capacity	C06	23.3	P
	C07	23.1	P
	C08	23.5	P
	C09	23.4	P
	C10	23.2	P

Notes 注释:

测试样品表面温度不超过 170 °C，测试中与测试后 6 小时内无解体、无破裂、无起火。Test sample external temperature does not exceed 170 °C and there is no disassembly, no rupture and no fire during the test and within six hours after the test.



T.7. 过度充电 Overcharge

样品状态 The state of samples	编号 No.	测试结果 Test result
在第一次循环完全充电状态 At first cycle, in fully charged states	B11	P
	B12	P
	B13	P
	B14	P
在25次循环结束后完全充电状态 After 25 cycles ending in fully charged states	B15	P
	B16	P
	B17	P
	B18	P

Notes 注释:
样品在测试中和测试后 7 天内无解体、无起火。There is no disassembly and no fire during the test and within seven days after the test.

T.8. 强制放电 Forced discharge

样品状态 The state of samples	编号 No.	测试结果 Test result
At first cycle, in fully discharged states 在第一次循环完全放电状态	C11	P
	C12	P
	C13	P
	C14	P
	C15	P
	C16	P
	C17	P
	C18	P
	C19	P
	C20	P
After 25 cycles ending in fully discharged states 在25次循环结束后完全放电状态	C21	P
	C22	P
	C23	P
	C24	P
	C25	P
	C26	P
	C27	P
	C28	P
	C29	P
	C30	P



Notes 注释:

样品在测试中和测试后 7 天内无解体、无起火。There is no disassembly and no fire during the test and within seven days after the test.





VII、样品图片 Sample Picture

电池 Battery



电芯 Cell





VIII、试验仪器设备清单 Test Equipment List

序号 No.	设备编号 Device No.	设备名称 Equipment name	设备型号 Equipment Model	有效期至 Calibration validity	本次使用 Used(√)
1	EP-B-001-01	电池低压高空模拟试验机	GX-3020-ZC50	2026-04-06	√
2	EP-B-004-01	电池重物冲击试验机	GX-5066-A	2026-04-07	
3	EP-B-003-01	电池挤压试验机	GX-5067-CSM	2026-04-07	√
4	EP-B-007-01	电池短路试验机	GX-6055-NT5	2026-04-07	√
5	EP-B-014-01	振动试验系统	JQA-031-150	2026-04-07	√
6	EP-B-015-01	高加速度冲击试验机	JQIS-25	2026-04-07	√
7	EP-B-017-02	电池充放电测试仪	CT-4008Tn-5V12A-S1	2026-04-07	√
8	EP-B-007-01	精密烤箱	GX-6055-NT5	2026-04-07	√
9	EP-B-022-01	万用表	FLUKE 15B+	2026-04-07	√
10	EP-S-042-12	直流电子负载测试仪	IT8510	2026-04-06	√
11	EP-B-020-01	可编程直流电源	62012P-80-60	2026-04-07	√
12	EP-B-031-01	电子天平称	PTX-JA510	2026-04-06	√
13	EP-S-030-01	恒温恒湿试验箱	XB-OTS-408H-C5	2026-04-07	√
14	EP-B-023-09	TP700多路数据采集仪	TP700	2026-04-07	√
15	EP-B-041-01	温湿度计	JR900	2026-04-09	√
16	EP-S-041-04	数显游标卡尺	MNT-150T	2026-04-06	√

声明

Statement

1、本报告无批准人、审核人及检测人签名和本单位检测专用章无效。

This report is invalid without the signature of the approver, reviewer and tester and the special seal for testing of Shenzhen Element Testing Co., Ltd.

2、本报告涂改和删除无效。

This report is invalid if is blotted out and deleted.

3、对检测报告若有异议，应于收到报告之日起十五天内向检测单位提出。

Objections to the test report must be submitted to Shenzhen Element Testing Co., Ltd. within 15 days.

4、本报告仅对本次客户所送测试样品有效。

This report is only valid for the test samples delivered by this customer.

5、未经深圳元素检测有限公司书面同意，不得部分地复制本报告

Nobody is allowed to photocopy or partly photocopy this test report without written permission of Shenzhen Element Testing Co., Ltd.

6、客户必须如实提供样品及资料，否则本单位不承担任何相关责任。

Customers must truthfully provide samples and data, otherwise we does not assume any relevant responsibilities.

--测试报告结束--

--End of test report--