



# Test Report

Report No. A2250849413102

Page 1 of 8

**Company Name shown on Report** TAIZHOU CITY HUANGYAN ZHENHUI PLASTIC MOULD CO., LTD.  
**Address** NO 41, YUMIN STREET, XINQIAN, HUANGYAN, TAIZHOU, ZHEJIANG PROVINCE

**The following sample(s) and sample information was/were submitted and identified by/on the behalf of the applicant**

Sample Name Baby Inflatable bath mat  
Sample Received Date Nov. 24, 2025  
Testing Period Nov. 24, 2025 to Dec. 3, 2025

**Test Conducted:**

As requested by the applicant. For details refer to next page(s)



Chen Kaimin  
Authorized Signatory

Centre Testing International Pinbiao(Shanghai) Co., Ltd.

Date Dec. 3, 2025 No. T172791892  
No.1351, Wanfang Road, Minhang District, Shanghai, China

# Test Report

Report No. A2250849413102

Page 2 of 8

**Executive Summary:**

**TEST REQUEST**

GB/T 42802-2023 Juvenile products-General requirements for bath washing supplies

**CONCLUSION**

**PASS\***

PASS\*=The inspection items selected by the customer meet the corresponding requirements, please refer to the inspection results page of this report.

For chemical test, the tested component(s) is/are identified by the applicant.

\*\*\*\*\* For further details, please refer to the following page(s) \*\*\*\*\*

# Test Report

Report No. A2250849413102

Page 3 of 8

**GB/T 42802-2023 Juvenile products—General requirements for bath washing supplies**

Clauses	Test items	Test results
5.1.1	Phthalates content	Pass See Note 1
5.1.2	Migration of certain elements	Pass See Note 2
5.1.3	AZO Colorants	Pass See Note 3
5.1.4	Short Chain Chlorinated Paraffins content	Pass See Note 4
5.1.5	Specific migration of Bisphenol A	Pass See Note 5
5.2.1	Restraint system	Pass
5.2.3	Moving components	Pass
5.2.4	Ropes	Pass
5.2.5	Small parts	Pass
5.2.8	Bathing cushion fasten on bath tub	Pass (See remark)
5.2.11.2	Static loading	Pass (See remark)

Remark: the clause 5.2.8 and 5.2.11.2 were tested based on the bath tub provided by client.

# Test Report

Report No. A2250849413102

Page 4 of 8

**Note 1:****▼ Phthalates content**

Test Method: GB/T 22048-2022 Method C; Test Equipment: GC-MS

Tested Item(s)	Result (%)	MDL	Limit
	001	(%)	(%)
Di-(2-ethylhexyl) phthalate (DEHP)	N.D.	0.001	--
Dibutyl phthalate (DBP)	N.D.	0.001	--
Butyl benzyl phthalate (BBP)	N.D.	0.001	--
Diisobutyl phthalate (DIBP)	N.D.	0.001	--
SUM (DEHP+ DBP+ BBP+DIBP)	N.D.	--	0.1
Di-isononyl phthalate (DINP)	N.D.	0.001	--
Di-n-octyl phthalate (DNOP)	N.D.	0.005	--
Di-iso-decyl phthalate (DIDP)	N.D.	0.005	--
SUM (DINP+DNOP+ DIDP)	N.D.	--	0.1

## Remark:

- MDL = Method Detection Limit
- N.D. = Not Detected (<MDL)

# Test Report

Report No. A2250849413102

Page 5 of 8

**Note 2:****▼ Migration of certain elements**

Test Method: GB 6675.4-2014; Test Equipment: ICP-OES

<u>Tested Item(s)</u>	<u>Result (mg/kg)</u>	<u>MDL(mg/kg)</u>	<u>Limit (mg/kg)</u>
	002		
Antimony (Sb)	N.D.	5	60
Arsenic (As)	N.D.	2.5	25
Barium (Ba)	N.D.	5	1000
Cadmium (Cd)	N.D.	5	75
Chromium (Cr)	N.D.	2.5	60
Lead (Pb)	N.D.	5	90
Mercury (Hg)	N.D.	2.5	60
Selenium (Se)	N.D.	5	500

## Remark:

- MDL = Method Detection Limit
- N.D. = Not Detected (<MDL)
- mg/kg = ppm = parts per million

# Test Report

Report No. A2250849413102

Page 6 of 8

**Note 3:**

**▼ AZO Colorants**

Test Method: GB/T 17592-2024; Test Equipment: GC-MS and/or HPLC

No	Tested Item(s)	CAS No.	Result (mg/kg)	LOQ (mg/kg)	Limit (mg/kg)
			002		
1	4-Aminodiphenyl	92-67-1	N.D.	5	20
2	Benzidine	92-87-5	N.D.	5	20
3	4-Chloro-O-Toluidine	95-69-2	N.D.	5	20
4	2-Naphthylamine	91-59-8	N.D.	5	20
5	O-Aminoazotoluene	97-56-3	N.D.	5	20
6	2-Amino-4-Nitrotoluene	99-55-8	N.D.	5	20
7	P-Chloroaniline	106-47-8	N.D.	5	20
8	2,4-Diaminoanisole	615-05-4	N.D.	5	20
9	4,4'-Diaminodiphenylmethane	101-77-9	N.D.	5	20
10	3,3'-Dichlorobenzidine	91-94-1	N.D.	5	20
11	3,3'-Dimethoxybenzidine	119-90-4	N.D.	5	20
12	3,3'-Dimethylbenzidine	119-93-7	N.D.	5	20
13	3,3'-Dimethyl-4,4'-Diaminodiphenylmethane	838-88-0	N.D.	5	20
14	P-Cresidine	120-71-8	N.D.	5	20
15	4,4'-Methylene-Bis(2-Chloroaniline)	101-14-4	N.D.	5	20
16	4,4'-Oxydianiline	101-80-4	N.D.	5	20
17	4,4'-Thiodianiline	139-65-1	N.D.	5	20
18	O-Toluidine	95-53-4	N.D.	5	20
19	2,4-Toluylenediamine	95-80-7	N.D.	5	20
20	2,4,5-Trimethylaniline	137-17-7	N.D.	5	20
21	O-Anisidine	90-04-0	N.D.	5	20
22	P-Aminoazobenzene	60-09-3	N.D.	5	20
23	2,4-Xylidine	95-68-1	N.D.	5	20
24	2,6-Xylidine	87-62-7	N.D.	5	20

# Test Report

Report No. A2250849413102

Page 7 of 8

**Remark:**

- LOQ = Limit of Quantification
- N.D. = Not Detected (<LOQ)
- mg/kg = ppm = parts per million

**Note 4:****▼ Short Chain Chlorinated Paraffins (SCCPs)**

Test Method: GB/T 41524-2022; Test Equipment: GC-MS

<u>Tested Item(s)</u>	<u>Result (%)</u>	<u>MDL(%)</u>	<u>Limit (%)</u>
	001		
Short Chain Chlorinated Paraffins (SCCPs)	N.D.	0.01	0.15

**Remark:**

- MDL = Method Detection Limit
- N.D. = Not Detected (<MDL)

**Note 5:****▼ Specific migration of Bisphenol A**

Test Method: SN/T 2407-2009; Test Equipment: HPLC

<u>Tested Item(s)</u>	<u>Result (mg/L)</u>	<u>MDL (mg/L)</u>	<u>Limit (mg/L)</u>
	001		
Bisphenol A (BPA)	N.D.	0.1	0.1

**Remark:**

- MDL = Method Detection Limit
- N.D. = Not Detected (<MDL)
- mg/L = Milligrams per liter

**Sample/Part Description**


No.	CTI Sample ID	Description
1	001	White plastic(buckle)
2	002	Grey tarp (main body)

# Test Report

Report No. A2250849413102

Page 8 of 8

## Photo(s) of the sample(s)



### Statement:

1. This report is considered invalid without approved signature, special seal and the seal on the perforation;
2. The Company Name shown on Report and Address, the sample(s) and sample information was/were provided by the applicant who should be responsible for the authenticity which CTI hasn't verified;
3. The result(s) shown in this report refer(s) only to the sample(s) tested;
4. Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019 / CNAS-GL015:2022;
5. Without written approval of CTI, this report can't be reproduced except in full;
6. In case of any discrepancy between the English version and Chinese version of the testing reports (if generated), the Chinese version shall prevail.

\*\*\* End of Report \*\*\*