

Test Report

Applicant : Dongguan Senland Industrial Co., Ltd.
Address : 6th Floor, Building C, No. 9, Junpu Industrial Road, Houjie Village,
Houjie Town, Dongguan
Manufacturer : Dongguan Senland Industrial Co., Ltd.
Address : 6th Floor, Building C, No. 9, Junpu Industrial Road, Houjie Village,
Houjie Town, Dongguan
Equipment Under Test (EUT)
Sample name : Beeswax Food Wrap
Testing type/model : N/A
Trademark : N/A
Received Date : 2024-05-11
Test Date : 2024-05-11 to 2024-05-16
Test requested : Selected test(s) as requested by client.
Test Method : Please refer to next page(s)
Test Results : Please refer to next page(s)

Result Summary:

Test Requested	Conclusion
1) US FDA 21 CFR 175.300: Resinous and polymeric coatings. - Chloroform-soluble extractives in Distilled water - Chloroform-soluble extractives in 8% Alcohol - Chloroform-soluble extractives in n-Heptane	Pass

***** For more detailed information, please refer to the next page*****

Approved by:



Results:**1) Chloroform Soluble Extractives****Test Method: with reference to US FDA 21 CFR 175.300**

Extractants and Conditions	MDL	Results	Permissible Limit (mg/inch²)
1.Chloroform soluble extractives, Distilled water at 250°F for 2 hours	0.3	10.7	≤18.0
2.Chloroform soluble extractives, 8% Alcohol at 150°F for 2 hours	0.3	15.2	≤18.0
3.Chloroform soluble extractives, n-Heptane at 150°F for 2 hours	0.3	16.8	≤18.0

Sample Description



1: Beeswax Food Wrap

Note:

1. mg/inch² = milligram per square inch.
2. °F = Degrees Fahrenheit.
3. MDL =Method Detected Limit

Appendix

Photograph of Sample



END OF REPORT